

2/pst

## IGNITION DEVICE AND METHOD FOR PRODUCING IT

~~Prior Art~~**BACKGROUND OF THE INVENTION**

5 The invention relates to an ignition device ~~as~~  
~~generically defined by the preamble to claim 1~~ and to a  
method for producing it.

10 Spark plugs essentially comprise a metal housing and an  
insert, which includes a ceramic insulator, a connection  
bolt, and a middle electrode. The steel materials used for  
the housing, for reasons of function, production and cost,  
corrode above all from the hot, corrosive atmosphere of the  
15 kind that occurs during operation in a vehicle. To protect  
against corrosion, the steel housing is typically coated with  
a metal layer.

20 As the metallizing layer, zinc or nickel is used, for  
instance. The anti-corrosion action of the zinc is based on  
the fact that as a less-noble metal, it corrodes instead of  
the iron and forms so-called white rust. This cathodic  
protection effectively prevents the iron from corroding. The  
formation of white rust is undesirable, however, from an  
25 aesthetic standpoint.

Nickel, which is a more-noble metal than iron  
electrochemically, can also be used to create an anti-  
corrosion layer. A problem then is that mechanical injuries  
30 to the protective layer lead to corrosion of the exposed iron  
and hence lead to the formation of so-called red rust. In  
German Patent DE-PS 38 41 215 C2, it is proposed that to  
prevent rust formation a chromate layer be applied to the  
nickel protective layer; the chromate layer covers the cracks

and pores in the protective layer. Chromate treatment involves major environmental risks, however.

~~Advantages of the Invention~~ **SUMMARY OF THE INVENTION**

5

The ignition device of the invention ~~as defined by the characteristics of the body of claim 1~~ has the advantage that the paint layer brings about effective corrosion protection that is durable even at elevated temperatures and is simple to achieve. For instance, a spark plug that has been

10 provided with a paint coating according to the invention exhibits no evidence of corrosion whatever even after a 100-hour salt-spray test.

15 With the provisions recited in the dependent claims, advantageous refinements of the ignition device according to the invention and the method according to the invention are possible.

20 For instance, the painting of the ignition device can be combined with other methods for corrosion protection, such as nickel-plating or zinc-plating. Furthermore, many painting methods are available that make it possible to adapt the painting process to the assembly of the ignition device.

25 The painting of the individual components is preferably done after they have been mounted on the finished ignition device.

It can be considered especially advantageous that with the aid of a paint coating, beyond the corrosion protection

30 not only can the visual appearance of the ignition device be improved but the sliding property, for instance, of a thread stamped onto the housing is also favorably affected.

~~Drawing~~

**BRIEF DESCRIPTION OF THE DRAWINGS**



22 comprise a multi-substance alloy based on nickel and for instance contain a copper core. However, it is also possible to use silver, platinum, or platinum alloys as electrode materials.

5

The housing 13 has a hexagon 14 on its outside that makes it possible to screw the spark plug into an engine block. An outer sealing seat 16 is also provided, which seals off the ambient atmosphere from the combustion chamber.  
10 The screw-in thread 18 stamped on the housing 13 serves to anchor the spark plug in the engine block.

Next to the hexagon 14, the housing 13 contains a shrinkage notch 15. During the production process of the spark plug, the housing 13 is briefly subjected to a high  
15 voltage. As a result, the shrinkage notch heats to temperatures of approximately 1200°C. At the same time, a high mechanical pressure is exerted on the housing 13 along the longitudinal axis of the spark plug, and under its effect  
20 the shrinkage notch 15 deforms. This operation is called hot pressing and serves to seal off the spark plug.

According to the invention, the corrosion protection of the metal components of the spark plug is brought about by  
25 applying a paint coating to the components that form the outer face of the spark plug. Paints that can be given primary consideration are heat-stable, moisture-proof and solvent-proof paints, which preferably harden under UV light to make fast curing of the paint possible. The paints are  
30 preferably colorless, or they can be provided with colored pigments.

For the painting 1 of the spark plug B to produce a painted spark plug C (see Fig. 2), various painting processes

can be considered. An example of an especially preferred method is a spray method in which the regions of the spark plug that are not to be painted are covered with a template, and the spark plug is rotated about its longitudinal axis during the process. Along with this method, known as templating, a combined spray and suction method, the so-called vacuumate technique, can be employed as an alternative. In it, the paint is sprayed in an aimed stream at the spark plug to be painted, and at the same time it is made highly turbulent by suction devices disposed next to the spray nozzle, and excess paint is immediately vacuumed away. Another especially suitable method that can be used is an ink-jet technique, in which an aimed stream of fine droplets is sprayed on in such a way that the droplets strike the surface close together.

The painting 1 of the spark plug is especially advantageously done, from a production standpoint, after the complete assembly a of the spark plug B from the components A. This makes it unnecessary to integrate painting units into production lines and furthermore makes it optionally possible to paint only those spark plugs that are intended for especially long service lives (long-life type), for instance. If the spark plug is produced by a hot pressing method, then painting prior to the assembly a would already be disadvantageous because as a result of the high temperatures occurring in the hot pressing, the paint layer would be damaged in the region of the shrinkage notch 15. If the spark plug is alternatively sealed off by a cold pressing method, then the components can also be painted individually before the assembly a of the spark plug B. In that case, the painting can also be done by means of immersion baths.

Depending on the requirements, it is possible to use a

combination of metallizing m and painting l as corrosion protection. Then, as shown in Fig. 2, the assembled spark plug B is first metallized m, and the metallized spark plug B' is then painted l, resulting in the metallized, painted spark plug C'. Direct painting l of the non-metallized spark plug B to make the spark plug C is also possible. The combination of metallizing m and painting l especially advantageously achieves better protection against mechanical damage to the anti-corrosion layer, since two protective layers are applied one above the other; conversely, omitting the metallizing m leads to improved adhesion of the painting l to the components to be protected against corrosion.

By the method according to the invention, all the components of the spark plug that are affected by corrosion can in principle be protected, if they are not exposed to a temperature of substantially more than 400°C. This applies especially to the housing 13, which is painted either including or not including the thread 18. Care must be taken that the paint used have sufficient friction resistance to the mechanical forces that engage the hexagon 14. Depending on requirements, painting of the connection means 11 is done in addition. This applies above all to the connection bolt 12 and the connection nut 19.

Painting the thread 18 can be considered especially advantageous, because here not only can the corrosion protection to the component be assured but moreover influence is exerted on the sliding properties of the component. This is an important aspect above all in spark plugs with a long service life, since after a long time in operation they can often be removed from the engine block again only with great difficulty.

The creation of corrosion protection by means of painting is not limited to spark plugs. For instance, glow plugs used in Diesel engines as an aid in starting, for instance, are similar in their design and can be equally effectively protected against corrosion with the aid of a paint coating.